

### Classe granulaire

8	14
---	----

### Partie contractuelle

Valeurs spécifiées sur lesquelles le producteur s'engage

#### Norme

Norme NF P 18-545 Article 10 - EN 12620 et EN 13139

#### Catégorie

CODE A


	0.063	0.5	3.15	d/2	4	5	5.6	6.3	d	8	10	11.2	12.5	D	14	16	20	1.4D	2D	f	
Etendue e										15					15						
Incertitude U					1					5					5		1				0.3
V.S.S.+U					6					25					100						1.80
V.S.S.					5					20					99						1.50
V.S.I.										0					80		98		100		
V.S.I.-U										0					75		97				
Ecart-type max																					

### Partie informative

#### Résultats de production

du 16/04/19 au 12/06/19

	0.063	0.5	3.15	4	5	5.6	6.3	8	10	11.2	12.5	14	16	20	28	f
Maximum	0.5	0	1	4		1	7	22	64	85	95	100	100	100	100	0.66
Xf+1.25xEcart-types		0	1			1	7		72	87	97		100			
Moyenne Xf	0.2	0	1	3	0	1	4	15	57	72	93	98	99	100	100	0.44
Xf-1.25xEcart-types		0	0			0	1		43	57	89		98			
Minimum	0.0	0	0	1		0	0	3	34	53	87	94	97	99	100	0.25
Ecart-type	0.20	0.1	0.4	1.5		0.3	2.3	7.2	11.6	11.8	3.2	1.9	1.2	0.5	0.0	0.110
Nombre de résultats	9	5	8	4	1	4	9	7	5	9	4	9	8	8	8	9



WIL 11.04.24.459 (c) Arcade

**Le Directeur du Laboratoire, G. BAUDIN**